

TECHNICAL INFORMATION

2501 BELLEZZA

TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	construction	ISO 2424	1/10" Cut pile
poolmateriaal	yarn content	ISO 2424	100% PA 6
rug	backing	ISO 2424	Comfort Backing
gebruiksklasse	suitability	EN 1307	23 / 32 medium contract use
poolinzetgewicht	pile weight	ISO 2424	2850 gr/m ²
totaal gewicht	total weight	ISO 8543	3750 gr/m ²
poolhoogte	pile height	ISO 1766	14,5 mm
totaal dikte	total thickness	ISO 1765	17 mm
noppental	tuft density	ISO 1763	263,000 tufts/m ²
breedte	width	CEN/TS 14159	ca. 4 m
warmte-doorlaatweerstand	thermal resistance	ISO 8302	0.19 m ² K/W
brandklasse	flammability	ISO 13501-1	Cfl-S1
contactgeluidsisolatie	impact sound insulation	ISO 140-8/717-2	25 dB
structure	Konstruktion	ISO 2424	1/10" Cut pile
composition	Polmaterial	ISO 2424	100% PA 6
dossier	Beschichtung	ISO 2424	Comfort Backing
classement d'usage	Zusatzeignung	EN 1307	23 / 32 medium contract use
poids de velours	Poleinsatzgewicht	ISO 2424	2850 gr/m ²
poids total	Gesamtgewicht	ISO 8543	3750 gr/m ²
hauteur du velours	Polschichtdicke	ISO 1766	14,5 mm
épaisseur totale	Gesamtdicke	ISO 1765	17 mm
densité	Noppenzahl	ISO 1763	263,000 tufts/m ²
dimensions	Breite	CEN/TS 14159	ca. 4 m
résistance thermique	Wärmedurchlasswiderstand	ISO 8302	0.19 m ² K/W
comportement au feu	Brandverhalten	ISO 13501-1	Cfl-S1
isolation acoustique	Trittschallverbesserungsma ß	ISO 140-8/717-2	25 dB

COLOURS

109 Pumice	152 Feldspar	189 Carbon
112 Panna Cotta	153 Gold	199 Ebony
119 Mist	154 Poplar	
132 Canvas	183 Talpa	
149 Cosy	184 Kalamata	

PRODIS RATING AND INFORMATION



EN 1307



PRODIS: CCFB0B3A

DOP: 1025-118793



CONTACT INFORMATION

BUCHAREST, ROMANIA
(HEAD OFFICE)
DR. PANAIT IATROPOL, NR. 22, 5TH DISTRICT
+40 747 228 553
office@carpetmore.ro
www.carpetmore.ro

geproduceerd door / manufactured for
fabriqué par / hergestellt durch

**CARPET &
MORE**
ROMANIA

Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.