

TECHNICAL INFORMATION

2176 DIVERSITY


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	construction	ISO 2424	1/10" woven look bouclé
poolmateriaal	yarn content	ISO 2424	100% Wool (triply)
rug	backing	ISO 2424	sbr free Actionbac®
gebruiksklasse	suitability	EN 1307	23 / 33 heavy contract use
poolgewicht	pile weight	ISO 2424	1200 gr/m ²
totaal gewicht	total weight	ISO 8543	2300 gr/m ²
pooldikte	pile height	ISO 1766	3.6 mm
totaal dikte	total thickness	ISO 1765	7.8 mm
noppental	tuft density	ISO 1763	90,000 tufts/m ²
breedte	width	CEN/TS 14159	ca. 4 m / ca. 5 m
warmtedoorlaatweerstand	thermal resistance	ISO 8302	0.13 m ² K/W
brandklasse	flammability	ISO 13501-1	Cfl-S1
contactgeluidsisolatie	impact sound insulation	ISO 140-8/717-2	25 dB
structure	Konstruktion	ISO 2424	1/10" woven look bouclé
composition	Polmaterial	ISO 2424	100% Wool (triply)
dossier	Beschichtung	ISO 2424	sbr free Actionbac®
classement d'usage	Zusatzeignung	EN 1307	23 / 33 heavy contract use
poids de velours	Poleinsatzgewicht	ISO 2424	1200 gr/m ²
poids total	Gesamtgewicht	ISO 8543	2300 gr/m ²
hauteur du velours	Polschichtdicke	ISO 1766	3.6 mm
épaisseur totale	Gesamtdicke	ISO 1765	7.8 mm
densité	Noppenzahl	ISO 1763	90,000 tufts/m ²
dimensions	Breite	CEN/TS 14159	ca. 4 m / ca. 5 m
résistance thermique	Wärmedurchlasswiderstand	ISO 8302	0.13 m ² K/W
comportement au feu	Brandverhalten	ISO 13501-1	Cfl-S1
isolation acoustique	Trittschallverbesserungsmaß	ISO 140-8/717-2	25 dB

COLOURS

121 Duck Egg	143 Ground Cumin	149 Hay Day	229 Old Age
122 Andean Quinoa	145 Sicilian Sumac	159 Stone Age	233 Flax Seed
139 Iron Powder	148 Steam Coal	212 Rolled Oats	

PRODIS RATING AND INFORMATION




 EN 14041
 EN 1307

 PRODIS: 8CDDE818
 DOP: 1025-122304



CONTACT INFORMATION

BUCHAREST, ROMANIA(HEAD OFFICE)
 DR. PANAIT IATROPOL, NR. 22, 5TH DISTRICT
 +40 747 228 553
 office@carpetmore.ro
 www.carpetmore.ro

geproduceerd door / manufactured for
 fabriqué par / hergestellt durch

CARPET & MORE
 ROMANIA

Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.