

TECHNICAL INFORMATION

2431 TAMINO


TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

constructie	construction	ISO 2424	1/10" super soft saxony
poolmateriaal	yarn content	ISO 2424	100% PA 6.6
rug	backing	ISO 2424	SBR free Starback
gebruiksklasse	suitability	EN 1307	23 / 32 general contract use
poolgewicht	pile weight	ISO 2424	1310 gr/m ²
totaal gewicht	total weight	ISO 8543	2300 gr/m ²
pooldikte	pile height	ISO 1766	7.0 mm
totaal dikte	total thickness	ISO 1765	10.4 mm
noppental	tuft density	ISO 1763	221,000 tufts/m ²
breedte	width	CEN/TS 14159	ca. 4 m
warmtedoorlaatweerstand	thermal resistance	ISO 8302	0.15 m ² K/W
brandklasse	flammability	ISO 13501-1	Bfl-s1 fully glued
contactgeluidsisolatie	impact sound insulation	ISO 140-8/717-2	25 dB
structure	Konstruktion	ISO 2424	1/10" super soft saxony
composition	Polmaterial	ISO 2424	100% PA 6.6
dossier	Beschichtung	ISO 2424	SBR free Starback
classement d'usage	Zusatzeignung	EN 1307	23 / 32 general contract use
poids de velours	Poleinsatzgewicht	ISO 2424	1310 gr/m ²
poids total	Gesamtgewicht	ISO 8543	2300 gr/m ²
hauteur du velours	Polschichtdicke	ISO 1766	7.0 mm
épaisseur totale	Gesamtdicke	ISO 1765	10.4 mm
densité	Noppenzahl	ISO 1763	221,000 tufts/m ²
dimensions	Breite	CEN/TS 14159	ca. 4 m
résistance thermique	Wärmedurchlasswiderstand	ISO 8302	0.15 m ² K/W
comportement au feu	Brandverhalten	ISO 13501-1	Bfl-s1 fully glued
isolation acoustique	Trittschallverbesserungsmaß	ISO 140-8/717-2	25 dB

COLOURS

112 Sugar	145 Fox	174 Loam
122 Sand	151 Water	181 Ocean
125 Rosedust	154 Olive Oil	189 Graphite
133 Taupe	159 Silt	
139 Marble	173 Deer	

PRODIS RATING AND INFORMATION



CE
EN 14041
EN 1307
Bfl-s1 DS
PRODIS:8B820CEA
DOP: 1025-124768



CONTACT INFORMATION

BUCHAREST, ROMANIA(HEAD OFFICE)
DR. PANAIT IATROPOL, NR. 22, 5TH DISTRICT
+40 747 228 553
office@carpetmore.ro
www.carpetmore.ro

geproduceerd door / manufactured for
fabriqué par / hergestellt durch

**CARPET &
MORE**
ROMANIA

Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.