

## TECHNICAL INFORMATION

2609 Zen Garden

### TECHNICAL SPECIFICATIONS ACCORDING TO EN 1307

|                         |                                 |              |                             |
|-------------------------|---------------------------------|--------------|-----------------------------|
| constructie             | <i>construction</i>             | ISO 2424     | 1/10" Level cut loop        |
| poolmateriaal           | <i>yarn content</i>             | ISO 2424     | Econyl PA6                  |
| rug                     | <i>backing</i>                  | ISO 2424     | SBR free Actionbac          |
| gebruiksklasse          | <i>suitability</i>              | EN 1307      | 23/33 heavy contract use    |
| poolgewicht             | <i>pile weight</i>              | ISO 2424     | 1250 gr/m <sup>2</sup>      |
| totaal gewicht          | <i>total weight</i>             | ISO 8543     | 2200 gr/m <sup>2</sup>      |
| poolhoogte              | <i>pile height</i>              | ISO 1766     | 6.0 mm                      |
| totaal hoogte           | <i>total height</i>             | ISO 1765     | 8.0 mm                      |
| noppental               | <i>tuft density</i>             | ISO 1763     | 271860 tufts/m <sup>2</sup> |
| breedte                 | <i>width</i>                    | CEN/TS 14159 | ca 4 m                      |
| rapport                 | <i>pattern repeat</i>           | CEN/TS 14159 | 50 x 50 cm                  |
| warmtedoorlaatweerstand | <i>thermal resistance</i>       | ISO 8302     | 0,09 m <sup>2</sup> K/W     |
| brandklasse             | <i>flammability</i>             | ISO 13501-1  | Cfl-s1                      |
| geluidsabsorptie        | <i>sound absorption</i>         |              | 25 DB                       |
| structure               | <i>Konstruktion</i>             | ISO 2424     | 1/10" Level cut loop        |
| composition             | <i>Polmaterial</i>              | ISO 2424     | Econyl PA6                  |
| dossier                 | <i>Beschichtung</i>             | ISO 2424     | SBR free Actionbac          |
| classement d'usage      | <i>Zusatzeignung</i>            | EN 1307      | 23/33 heavy contract use    |
| poids de velours        | <i>Poleinsatzgewicht</i>        | ISO 2424     | 1250 gr/m <sup>2</sup>      |
| poids total             | <i>Gesamtgewicht</i>            | ISO 8543     | 2200 gr/m <sup>2</sup>      |
| hauteur du velours      | <i>Polschichthöhe</i>           | ISO 1766     | 6.0 mm                      |
| hauteur totale          | <i>Gesamthöhe</i>               | ISO 1765     | 8.0 mm                      |
| densité                 | <i>Noppenzahl</i>               | ISO 1763     | 271860 tufts/m <sup>2</sup> |
| dimensions              | <i>Breite</i>                   | CEN/TS 14159 | ca 4 m                      |
| raccord                 | <i>Rapport</i>                  | CEN/TS 14159 | 50 x 50 cm                  |
| résistance thermique    | <i>Wärmedurchlasswiderstand</i> | ISO 8302     | 0,09 m <sup>2</sup> K/W     |
| comportement au feu     | <i>Brandverhalten</i>           | ISO 13501-1  | Cfl-s1                      |
| absorption acoustique   | <i>Shallabsorptiongrad</i>      |              | 25 DB                       |

### COLOURS

|             |              |
|-------------|--------------|
| 102 Pearl   | 179 Peat     |
| 112 Papyrus | 194 Kalamata |
| 122 Salt    |              |
| 133 Taupe   |              |
| 136 Camel   |              |

### PRODIS RATING AND INFORMATION



EN 14041

EN 1307



BY AQUAFIL



carpet that cares

### CONTACT INFORMATION

BUCHAREST, ROMANIA(HEAD OFFICE)  
DR. PANAIT IATROPOL, NR. 22, 5TH DISTRICT  
+40 747 228 553  
office@carpetmore.ro  
www.carpetmore.ro

geproduceerd door / manufactured for  
fabriqué par / hergestellt durch

**CARPET &  
MORE**  
ROMANIA

Alle technische specificaties zijn onderhevig aan productietoleranties. Voor alle voorwaarden en onderhoudsadvies verwijzen wij u graag naar onze website.

All specifications are subject to normal manufacturing tolerances. For all Terms & Conditions, care and maintenance, please visit our website.

Toutes les spécifications techniques sont sujet aux tolérances de fabrication. Merci de consulter notre website pour toutes informations et les conseils d'entretien.

Alle technische Daten unterliegen Produktionstoleranzen. Bedingungen und Pflegeempfehlungen finden Sie auf unserer Website.

v2